



Compressed fiber	Flexseals 330
<b>Composition</b>	High quality mineral and aramid fibres with NBR binder
<b>Minimum density DIN 28090-2</b>	1.7 g/cm <sup>3</sup>
<b>Maximum density DIN 28090-2</b>	2.0 g/cm <sup>3</sup>
<b>Maximum operating temperature</b>	330 °C
<b>Max recommended Peak Temperature</b>	450 °C
<b>Leakage DIN 3535-6</b>	0.04 mg*s-1*m-1
<b>Residual Stress* 16h/175 °C Din 52913</b>	32 Mpa
<b>Compressibility ASTM F 36-J</b>	5-15 %
<b>Recovery ASTM F 36-J min.</b>	50 %
<b>ASTM OIL -IRM 903 5h/150 °C max ASTM F 146</b>	3 %
<b>ASTM FUEL B 5h/23 °C max ASTM F 146</b>	5 %
<b>Available sheets size</b>	1500x1500 mm 1500x3000 mm
<b>Available thickness</b>	from 0.5 to 5 mm
<b>Sheet size tolerance</b>	50 mm
<b>Thickness tolerance</b>	10 %



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.