



XGD® 16 a glass fibers reinforced thermosetting plastic with filler content.

Special Material Characteristics

- high continuous usage temperature
- excellent mechanical strength
- good insulation effect

Range of Applications

XGD® 16 is preferred to use in applications in the tool and mould making industry where a good insulation effect and a high mechanical strength is required.

Property	Value	Unit
Max. Service Temperature	180	°C (long-term)
	200	°C (short-term)
Compressive Strength	340	N/mm ² (at ambient temperature)
	130	N/mm ² (at 200°C)
Coefficient of Thermal Conductivity	0.18	W/mK (at ambient temperature)
	0.23	W/mK (at 200°C)
Linear Coefficient	20×10^{-6}	1/K (X- and Y-direction)
	150×10^{-6}	1/K (Z-direction)
Flexural Strength	115	N/mm ² (at ambient temperature)
	55	N/mm ² (at 200°C)
Density	1.70	g/cm ³



The information in this publication, as well as any additional information provided to users, is based on experience and is shared to the best of our current knowledge. However, due to numerous factors beyond our knowledge and control that may affect the use of these products, no warranties are provided or implied regarding this information. The operating limits presented in this publication do not imply that these values can be applied simultaneously. Do not use the product at the maximum temperature and pressure values simultaneously. The maximum temperature is suitable only for short-term exposure under specific conditions. Specifications are subject to change without prior notice. The picture in the DS may not accurately depict the exact color and/or markings of the product.

Planichem s.r.l.

Via Consolare 41/43 25030 Zocco di Erbusco (BS) - ITALY

Tel: +39 030 7386033 - www.planichem.com - info@planichem.com